PRIMEX P 200

Polyvinyl chloride for thermoplastic processing

PRIMEX P 200 is a homopolymer PVC resin manufactured by the suspension polymerization process. It has a low to medium molecular weight and is characterized by good mechanical properties.
ASTM D 1755 classification.

Application	rigid	flexible
Films & Sheets	●	
Flooring	●	
Others	●	
Profiles & Pipes	❍	
Sealants	❍	
Textile Coatings		
Wire & Cables		

● recommended ❍ feasible ■ additive

Property	Method	Unit	Value *1
K value	DIN EN ISO 1628-2	-	61
Inherent Viscosity (IV)	ASTM D 1243-95	dL/g	0.78
Apparent Density	ASTM D 1895-96	g/cm³	≥ 0.51
Particle Size - retained on sieve #40	ASTM D 1921-96	%	≤ 0.04
Particle Size - retained on sieve #60	ASTM D 1921-96	%	≤ 5
PAN	ASTM D 1921-96	%	≤ 7
Fish-eyes	ASTM D 3596-92	#/dm²	≤ 35
Volatile Matter	ASTM D 3030-11	%	≤ 0.3
Residual Vinyl Chloride Monomer	ASTM D 3749-13	mg/kg	≤ 1

*1: The figures quoted above are typical values, and do not form part of the specification.

PRIMEX P 200

Processing

PRIMEX P 200 is a low-medium molecular weight resin offering good processing conditions and good thermal stability.

Recommended for rigid applications that require good mechanical properties when fold during thermoforming and low Fish eyes content.

Applications are

- Films & Sheets (Rigid Films and Sheets)
- Flooring
- Profiles & Pipes (Decking / Fences, Fittings, Sidings, Technical Profiles)
- Sealants
- Others (Bottles, Medical Devices)

Processing methods include

- Blow Molding
- Extrusion
- Calendering
- Injection Molding

Packaging, Delivery

in bags (25 kg), supersacks (700 kg, 1,400 kg), bulk, hopper-car or railway-hopper.

Storage

The recommended storage conditions for the material are:

- Dry environment
- Not in the vicinity of direct or indirect heat sources

Shelf-life

According to the available experience, PVC can be stored almost without restrictions and can be used for months to several years if stored properly. We recommend consumption within one year after delivery.

Safety

Please refer to the current safety data sheet for the safety precautions necessary for handling.

General Notes

For further information and advice, please contact our technical service at Technical-Service.LATAM@vestolit.com or our representatives.

This information is based on our present knowledge and experience. However, it does not imply liability or other legal responsibility on our part, including, in particular, existing third-party patent rights. No guarantee of properties in the legal sense is implied. We reserve the right to make any change according to technical progress of further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Reference to trade names and other companies is not a recommendation and does not exclude the use of similar products.