PRIMEX P 225-2

Polyvinyl chloride for thermoplastic processing

PRIMEX P 225-2 is a homopolymer PVC resin manufactured by the suspension polymerization process. It has a medium molecular weight and is characterized by good color, high flow during extrusion process and good thermal stability.
ASTM D 1755 classification.

Application	rigid	flexible
Films & Sheets	❍	
Flooring	❍	
Others	●	
Profiles & Pipes	●	
Sealants	❍	
Textile Coatings		
Wire & Cables		

● recommended ❍ feasible ■ additive

Property	Method	Unit	Value *1
K value	DIN EN ISO 1628-2	-	66
Apparent Density	ASTM D 1895-96	g/cm³	≥ 0.54
Particle Size - retained on sieve #40	ASTM D 1921-96	%	≤ 0.05
Particle Size - retained on sieve #60	ASTM D 1921-96	%	≤ 7
PAN	ASTM D 1921-96	%	≤ 4
Pourability	ASTM D 1895-96	s	≤ 23
Volatile Matter	ASTM D 3030-11	%	≤ 0.3
Residual Vinyl Chloride Monomer	ASTM D 3749-13	mg/kg	≤ 1

*1: The figures quoted above are typical values, and do not form part of the specification.

PRIMEX P 225-2

Processing

PRIMEX P 225-2 is a medium molecular weight resin offering high flow during extrusion process and good thermal stability.

Recommended for rigid applications that require good mechanical properties and good color.

Applications are

- Films & Sheets (Rigid Films and Sheets)
- Flooring (Luxury Vinyl Tiles (LVT), Other floorings)
- Profiles & Pipes (Decking / Fences, Pipes, Sidings, Technical Profiles, Window Profiles)
- Sealants
- Others

Processing methods include

- Blow Molding
- Extrusion
- Injection Molding

Packaging, Delivery

in bags (25 kg), supersacks (700 kg, 1,000 kg, 1,400 kg), bulk.

Storage

The recommended storage conditions for the material are:

- Dry environment
- Not in the vicinity of direct or indirect heat sources

Shelf-life

According to the available experience, PVC can be stored almost without restrictions and can be used for months to several years if stored properly. We recommend consumption within one year after delivery.

Safety

Please refer to the current safety data sheet for the safety precautions necessary for handling.

General Notes

For further information and advice, please contact our technical service at Technical-Service.LATAM@vestolit.com or our representatives.

This information is based on our present knowledge and experience. However, it does not imply liability or other legal responsibility on our part, including, in particular, existing third-party patent rights. No guarantee of properties in the legal sense is implied. We reserve the right to make any change according to technical progress of further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Reference to trade names and other companies is not a recommendation and does not exclude the use of similar products.